

| Identifikation | Styrke | | | Duktilitet | | Betegnelse |
|----------------|-------------------|--------|-----|--------------------|----------|------------|
| | Fyk \geq (MPA) | Klasse | | Ajk \geq (%) | (ft/fy)k | |
| N | 500 | B500 | 2,5 | $\geq 1,05$ | A | B500A |
| K | 500 | B500 | 5,0 | $\geq 1,08$ | B | B500B |
| Z | 500 | B500 | 7,5 | $\geq 1,15 < 1,35$ | C | B500C |
| Y | 550 | B550 | 5 | $\geq 1,08$ | B | B550B |
| | 550 | B550 | 2,5 | $\geq 1,05$ | A | B550A |
| | 550 | B550 | 7,5 | $\geq 1,15 < 1,35$ | C | B550C |